NC/QC/YPD/SIP-05/2018-19/KL-CB5

Date: 24-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-04-18	24-04-18	07	22500	380	16.89	**16.67**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	360	16.00	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/YPD/SIP-05/2018-19/KL-CB6

Date: 25-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-04-18	25-04-18	07	22500	390	17.33	**17.33**
	002	"	"	"	"	395	17.56	
	003	"	"	"	"	385	17.11	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/YPD/SIP-05/2018-19/KL-CB7

Date: 25-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	18-04-18	25-04-18	07	22500	360	16.00	**16.37**
	002	"	"	"	"	375	16.67	
	003	"	"	"	"	370	16.44	

*As Furnished by Client.
The Results relate only to the items tested.

K...R
KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

Newzen Consultants Bangalore

NC/QC/YPD/SIP-05/2018-19/KL-CB8

Date: 26-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	19-04-18	26-04-18	07	22500	400	17.78	**17.48**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	395	17.56	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2018-19/KL-CB9

Date: 26-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	19-04-18	26-04-18	07	22500	395	17.56	**16.81**
	002	"	"	"	"	375	16.67	
	003	"	"	"	"	365	16.22	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187

NC/QC/YPD/SIP-05/2018-19/KL-CB10

Date: 27-04-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	20-04-18	27-04-18	07	22500	395	17.56	**16.96**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	365	16.22	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN
M.E, (Civil

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2018-19/KL-CB2A

Date: 14-05-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-04-18	14-05-18	28	22500	535	23.78	**23.26**
	002	"	"	"	"	510	22.67	
	003	"	"	"	"	525	23.33	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

NC/QC/YPD/SIP-05/2018-19/KL-CB3A

Date: 14-05-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{*Project**: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-04-18	14-05-18	28	22500	535	23.78	**23.56**
	002	"	"	"	"	525	23.33	
	003	"	"	"	"	530	23.56	

*As Furnished by Client.
The Results relate only to the items tested.

AE

Page No. 1/1,

KIRAN. R
M.E, (Civil-Engg)

For Newzen Consultants Bangalore
Proprietor

NC/QC/YPD/SIP-05/2018-19/KL-CB4A

Date: 15-05-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-04-18	15-05-18	28	22500	545	24.22	**24.00**
	002	"	"	"	"	540	24.00	
	003	"	"	"	"	535	23.78	

*As Furnished by Client.
The Results relate only to the items tested.

Proprietor

Newzen Consultants Bangalore

NC/QC/YPD/SIP-05/2018-19/KL-CB5A

Date: 15-05-2018

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements Road and Drain at Kogilu layout in Ward No. 05.}
Ref.: Material testing/PMC/17-18,
Report Required for: Assistant Executive Engineer,
Yelahanka Project Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

AE

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-04-18	15-05-18	28	22500	530	23.56	**24.07**
	002	"	"	"	"	545	24.22	
	003	"	"	"	"	550	24.44	

*As Furnished by Client.
The Results relate only to the items tested.

KIRAN. R
M.E, (Civil-Engg)

AE

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com